

# 絲 導 表 面 粗 度

## The Roughness of Bell's Ceramic Yan Guides

Code	說明 Description
N	一般拋光處理, Ra=0.1-0.2 $\mu\text{m}$ Normal finish, Ra=0.1-0.2 $\mu\text{m}$
M	無光處理, Ra=0.2-0.3 $\mu\text{m}$ Matt finish, Ra=0.2-0.3 $\mu\text{m}$
L	平面研磨處理, Ra=0.25-0.35 $\mu\text{m}$ Lapping finish, Ra=0.25-0.35 $\mu\text{m}$
P	鑽石拋光處理, Ra=0.04 $\mu\text{m}$ Diamond finish, Ra=0.04 $\mu\text{m}$
HF	梨地處理, Ra=0.25-0.5 $\mu\text{m}$ ,適用於 ASO Matt overfitting finish, Ra=0.25-0.5 $\mu\text{m}$ ,for ASO
MF	一般梨地處理, Ra=0.3-0.4 $\mu\text{m}$ , 適用於 ASF Matt overfitting finish, Ra=0.3-0.4 $\mu\text{m}$ , for ASF
PF	鑽石拋光後梨地處理, Ra=0.2-0.3 $\mu\text{m}$ , 適用於 ASF Diamond finish and then matt overfiring finish, Ra=0.2-0.3 $\mu\text{m}$ ,for ASF